

## MATERIAL SPECIFICATION

VOCAB NUMBER	ITEM DESCRIPTION
111011	CABLE, 2 X 7/1.70 COPPER, HARD DRAWN PVC INSULATED, TWO CORE, AERIAL SERVICE, 16MM <sup>2</sup>

### SPECIFICATION DETAILS

Two core twisted, hard-drawn copper, PVC insulated, aerial cable in accordance with Table 12 of 3147 – AS/NZ 5000.1 2005.

Conductor Area: 2 - Core, 16mm<sup>2</sup>, (2 X 7/1.04)

Conductor Material: Hard-drawn Copper

Insulation: V – 90, Black

Packing Length: 1,000m

The Cable shall be supplied on Timber Drums in accordance with the attached general specification.

Attention is drawn to the requirements in clause 7.

- **Unit of Measure:** Metre
- **Rejection:** PNG Power Ltd reserves all rights to reject whole or part of the order not complying with this specification and is not liable for any cost or loss with the return of rejects to the Supplier. Facilitation of Invoice Credit must commence between the supplier and PNG Power Ltd through the process of PNG Power Ltd Discrepancy Report provisions.

**Drawing References:** N/A

**Manufacturer's Product Code:**

### STANDARDS COMMITTEE APPROVAL

Approval by Grevasius Peni:  
Chairman

Signature: 

Date: 25 / 9 / 18

### DATA REVIEW ENDORSEMENT

NAME	TITLE	SIGNATURE	DATE
Rawali Rawali	Engineer - Standards and Materials		25/09/18
G. PENI	TL STANDARDS		04/10/21

**SPECIFICATION DETAILS FOR VOCAB 111011**

1. All drums shall comply with AS 2857 "Timber Drums for Insulated Electric Cables and Bare Conductors" and the last amendments.
2. The net contents of any drum shall not exceed the capacity limits of clause 2.1.1 of AS 2857.
3. Spindle holes shall be reinforced with steel plates in accordance with clause 2.5 of AS 2857.
4. All drums other than those with plywood flanges shall be supplied with close fittings timber batten lagging in accordance with clause 6.3 of AS 2857.
5. Drums intended to be used for bare aluminium based conductors shall be evenly coated on the barrel and inside flanges with an aluminium paint or approved alternative. See clause 6.1 AS 2857.
6. Drums intended to be used for underground cables shall be fabricated from preservative treated timber.
  - 6.1 Preservative treatment of timber shall comply with the requirements of Australian standard AS 1604 "Preservative-Treated Sawn Timber, Veneer and Plywood.
  - 6.2 Timber shall be seasoned to 30% moisture content or less and shall be Vacuum-pressure impregnated with recognised waterborne CCA preservative Prior to construction and assembly of the drum.
  - 6.3 Preservative treatment shall comply with the minimum retention specified for Hazard level H5 (outdoor, unpainted, moderate) as set out in table 2 of AS 1604.
7. Drums shall be marked as follows with: -
  - a) As required by AS 2857.
  - b) A description of the construction of the cable and conductors.
  - c) The conductor material and the conductor cross-section
  - d) The number of cores if applicable
  - e) The voltage rating of the cable (if applicable)
  - f) The length of cables or conductor on the drum.
  - g) The gross mass of the drum and contents,
  - h) An arrow with the words "ROLL THIS WAY" to indicate the direction in which the drum shall be rolled on the flanges.
  - i) The PNG Power vocabulary numbers as shown on the particular material specification.

**NB:** Additional marking may be required by the particular material specification. This should be read in conjunction with this clause.